

Manufacturer	Mox Profile Systems
Product Name	Scala R
Product Description	Aluminium non-slip step nose protection
Product No	3379
Document Title	Design and quality of Scala R


Scala-R aluminium non-slip step nose protection is mostly preferred in public areas with too much human traffic. It provides maximum protection against accidents with its non-slip PVC attachment. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing, and with its pretreatment application that provides resistance to corrosion in electrostatic powder painting. Scala-R provides unity to step covering materials with its plain, minimal design. Scala-R aluminium non-slip step nose protection can be easily installed by adhering or screwing the profile to flooring according to its material. It is available in 2700mm length and 53x32mm size. Scala-R aluminium non-slip step nose protection has matte anodized, bright anodized, satin chemical bright anodized and electrostatic powder painting options. While silver, yellow, inox, bronze and black anodized color coatings are available, it can also be painted to the desired RAL code with electrostatic powder painting.



Warranty

Mox Profile Systems presents to your information that all our aluminium profile materials have been under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



Technical Details

Material:	Aluminium
Height:	33 mm
Width:	54 mm
Length:	2700 mm
Alloy:	EN AW 6463 T6, EN AW 6061 T6
Surface:	Powder Coated, Anodised, Chrome Plated

Manufacturer Quality Certifications



Important Note

THIS PRODUCT HAS BEEN DESIGNED BY MOX PROFILE SYSTEMS AT THE REQUEST OF THE CUSTOMER. MOX PROFILE SYSTEMS CANNOT BE HELD RESPONSIBLE FOR ANY INFRINGEMENT OF PATENTS, COPYRIGHTS OR OTHER SUCH CONDITIONS RELATED TO THE DESIGN

ALLOY DATA SHEET
EN AW 6463 (AlMg0,7Si)

Place of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, façade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20-60	Max 0,15	0,2	Max 0,5	045 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Proof Stress	Tensile Stress	Elongation		Brinell Hardness
				Min	Max	
	e*mm	R _{p0.2} min Mpa	R _m min Mpa	A _{50mm} %	A %	HB**
T4	e≤50	75	125	14	12	46
T5	e≤50	150	110	8	6	60
T6	e≤50	195	160	10	8	74

*Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged.

** Hardness values are for indication only

***For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section

Physical properties (approximate values, 20°C)

Density	Melting range	Electrical conductivity	Thermal conductivity	Co-efficient of thermal expansion	Modulus of elasticity
[kg/m ³]	[°C]	[MS/m]	[W/m.K]	10 ⁻⁶ /K	[GPa]
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5 and T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative/bright/colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6 – unsuitable